



TEST REPORT

Report No. : MAN:HL:7480006683

DATE : 22nd Aug, 2016



ALUDECOR LAMINATION PVT LTD..
1RN MUKHERJEE ROAD 5th FLOOR, SUITE NO- 52
KOLKATA-70001
INDIA
CONTACT PERSON : MR. PRASHANT OJHA

THE FOLLOWING SAMPLE(S) WAS/WERE SUBMITTED AND IDENTIFIED BY/ON BEHALF OF THE CUSTOMER AS :

SAMPLE DESCRIPTION ALUMINIUM COMPOSITE PANEL
COUNTRY OF ORIGIN INDIA
SAMPLE RECD ON 01/07/2016
TEST PERFORMING DATE 07/07/2016 TO 17/08/2016



SUMMARY OF TEST RESULTS:

TEST REQUESTED	CONCLUSION
DEFLECTION TEMPERATURE UNDER LOAD	SEE RESULT

Per Pro SGS India Pvt Ltd.

Subasini Saraswat
Asst. Manager
Email your Test Report Related Enquiries at Feedback.HLT@sgs.com

TEST REPORT

Report No. : MAN:HL:7480006683

DATE : 22nd Aug, 2016




TEST NAME & METHOD	RESULTS
DEFLECTION TEMPERATURE UNDER LOAD ASTM D648-07 Method A/B	116.5°C

Note:

- °C= Degree Celcius
- Testing has been performed as per client's request.
- Testing has been subcontracted to SGS approved lab.

Sample as Received



*****End of Report*****